



PA12	Value	Unit
Tensile Strength	50	MPa
Young Module	1850	Mpa
Elongation at Break	12	%
HDT	154	°C

PA11	Value	Unit
Tensile Strength	48	MPa
Young Module	1560	Mpa
Elongation at Break	35	%
HDT	130	°C

DISCLAIMER

The Information presented herein has been compiled from sources considered to be dependable and is accurate to the best of our knowledge. However, since data, safety standards, and government regulations are subject to change and the conditions of handling and use, or misuse, are beyond our control, Caracol S.R.L. makes no warranty expressed or implied, with respect to completeness or continuing accuracy of the information contained herein and disclaims all liability for reliance thereon.

User should satisfy himself that he has all current data relevant to his particular use.